

UV7160 Gloss Primer FCM

DESCRIPTION

Food packaging compliant (FPC) UV flexo gloss primer for non-direct food contact packaging applications as well as general label printing.

PROPERTIES

- ✓ Excellent adhesion properties
- ✓ Fast cure
- ✓ Excellent printability
- ✓ Excellent chemical resistance
- ✓ Offering improved adhesion of subsequently printed UV curable inks on a wide variety of substrates
- ✓ Formulated for non-direct food contact packaging applications

SUBSTRATES

Suitable for a wide range of coated papers, films and label stocks including:

- ✓ Coated PE and PP
- ✓ Aluminium foils
- ✓ PET, OPP, BOPP

The suitability of uncoated synthetic substrates such as PP should be tested before printing. The surface tension should be 38 dyne/cm or above. Corona treatment should be considered to improve the wetting and adhesion onto the substrate.

APPLICATION

Mix well before use.

Anilox Selection:

120-160 l/cm (300-450 lpi) volume 4-8 cm³/m²

Minimum lamp power – 160 W/cm

Fully cured UV flexo primers will obtain resistance properties 24 hours after printing.

Note: The risk of migration is increased if the primer is not fully cured.

Clean equipment immediately after use.

RESPONSIBILITY

This product has been formulated to comply with the regulations and guidelines for non-direct food contact packaging applications. However, it is the responsibility of the seller of the finished product to ensure all members of the packaging chain comply with recommended guidelines and regulatory requirements.

The risk of any contamination affecting food packaging applications should be assessed prior to use.

This technical instruction sheet is designed for your information and reference. It is based on and conforms to our current knowledge. However as actual application is affected by many factors over which we have no control, we are not liable for printing failures.

**STORAGE &
HANDLING**

Containers should be tightly closed immediately after use. All products, including uncontaminated press returns and unopened containers, should be stored at temperatures between 5°C and 25°C.

Shelf life is 6 months from date of manufacture (as indicated on the label).

HEALTH & SAFETY

Please refer to relevant SDS for information on labelling classifications, waste product and container disposal, and personal protection measures.

**AUXILIARY
PRODUCTS**

Cleaner: RLA350 UV Wash

Note: The addition of auxiliary products to the FPC primers may have a negative effect on levels of migration.

DISCLAIMER

The information contained in this data sheet is correct to the best of our knowledge. It is intended as a guide only for the optimum use of the named product(s) and is not intended as a warranty or as a specification. The product(s) included in this datasheet may not be suitable for use with other materials or in processes other than those specifically described. The user(s) should always make their own tests to establish that the product(s) meets their specification and complies with any appropriate guidelines or regulatory requirements.

This technical instruction sheet is designed for your information and reference. It is based on and conforms to our current knowledge. However as actual application is affected by many factors over which we have no control, we are not liable for printing failures.